

UltraWeld E6013

APPROVAL:

Classifications: AWS/A5.1E6013
IS814:ER4221

Characteristics:

UltraWeld E6013 is a medium coated general purpose Mild steel Electrode. Easy to operate well on AC/DC in all position except vertical Down. The Electrode gives excellent arc stability and very easy slag Removal. Weld Metal is of good Mechanical properties and Radiographic quality.

Application:

Welding of Mild steel for structural welding, Bus & Truck body building, Grills, steel furniture, steel tanks, frames, pipes, Maintenance and repair in mild steel etc.

Welding Polarity: DC ± AC50 volt

Size-mm	Ø2.50 X 350	Ø3.15 X 350	Ø4.00 X 450	Ø5.00 X 450
Current-amps	60-90	100-130	140-190	190-240

All weld metal chemical composition:

Element	Minimum %	Maximum%
Carbon	-	0.10
Manganese	0.35	0.60
Silicon	0.15	0.30
Sulphur	-	0.03
Phosphorous	-	0.03

All weld metal mechanical properties:

Description	Minimum	Maximum
Yield strength-N/mn ²	330	-
Tensile strength-N/mn ²	410	540
Elongation% on GL=5.65 Square root of area	22	-
Chrpy V-Notch Impact, Value at 0°C Joules	47 Joules	-

Coating Ration: Over 1.30 up to and including 1.50

Radiography: Grade 2 as per IS:814-2004

